



PRORAPID RS

Rapid Set Flexible Tile Adhesive

Features

- High strength
- Frost-resistant
- Suitable for:
 - Porcelain & natural stone tiles
 - Underfloor heating
 - Floors & walls
 - Internal & external use

Ultra Tile ProRapid RS premium grade cementitious tile adhesive ideal for natural stone, porcelain and ceramic tiles where exceptional bond and rapid set are essential.



3-12 mm

BED THICKNESS

1 HR

POT LIFE

2.5 HRS

SET TIME

LIFETIME GUARANTEE

C2 FT

MANUFACTURED TO MEET EN12004 CLASSIFICATION



Rapid Set Flexible Tile Adhesive

Ultra Tile ProRapid RS premium grade cementitious tile adhesive ideal for natural stone, porcelain and ceramic tiles where exceptional bond and rapid set are essential. A polymer modified adhesive for increased bond strength and enhanced performance. It is suitable for both wet and dry conditions and formulated to adhere to most common substrates including screwed and fixed over-boarded wooden floors (15mm minimum).

SURFACE PREPARATION

The surface being adhered to must be clean, firm, dry, free of dust, dirt, oils and grease and be strong enough to support the weight of the adhesive and tiles being fixed. To encourage best adhesion to your substrate it is advisable when applying adhesive to porous surfaces that the area is primed. Ultra Tile Prime IT FP is an ideal surface primer, as it will help to prevent water penetration, and increase bond strength. On non-porous surfaces use the recommended Ultra Floor primer from the Prime IT range.

MIXING

Ultra Tile ProRapid RS should be added slowly to clean water and mixed thoroughly to give a slump free easily worked mortar. Once mixed the mortar is immediately ready to use and has a pot life of approximately 1 hour at 20°C. Mix only sufficient material to be used within the pot life, do not remix or re-wet. Approx. mixing ratio of 4.2-4.5 litres per 20kg.

APPLICATION

Apply the adhesive to a thickness of 3mm-12mm up to 1m² at a time. On internal walls use a notched trowel, leaving solid ribs i.e. 3mm x 3mm at 6mm centres for mosaics, 5mm x 5mm at 10mm centres for wall tiles and 8mm x 8mm at 16mm for floor tiles. On floors and external areas, use the solid bed trowel method. Large studded tiles should be 'buttered'. Bed the tiles in with a slight twisting action. Leave spaces between the tiles for grouting (approximately 1mm-3mm for walls and 2mm-20mm for floors). Clean off excess adhesive from the tile face and grout lines with a damp cloth before it sets.

CLEANING

Tools should be thoroughly cleaned in water to remove excess material immediately after use.

GROUTING

Tile set may be affected by temperature and conditions, meaning, so too will the grouting start time. Check the set time before grouting. Please call Instarmac for the recommended Ultra Tile grout.

QUALITY ASSURANCE

All products are manufactured in a plant whose quality management system is certified/registered as being in conformity with BS EN ISO 9001, ISO 14001 and OHSAS 18001. Ultra Tile products are guaranteed against defective materials and manufacture and will be replaced or money refunded if the goods do not comply with our promotional literature. We cannot however accept responsibility arising from the application or use of our products because we have no direct or continuous control over where and how our products are used. All Ultra Tile products are sold subject to our terms and conditions of sales, copies of which may be obtained upon request.

TECHNICAL DATA

Packaging:	20kg bags
Standard Conformity:	EN 12004 Class C2 FT
Bed Thickness:	3mm-12mm
Coverage:	3mm bed thickness you will require 4.5kg of material per m ²
Pot Life:	1 hour depending upon temperature and substrate
Set Time:	2.5 hours dependent upon temperature and substrate

Storage: This product must be stored in unopened bags, clear of the ground in cool dry conditions and protected from excessive drafts. If stored correctly and used within 12 months of the date shown on the bag, the activity of the reducing agent will be maintained and this product will contain, no more than 0.0002% (2ppm) soluble Chromium (VI) of the total dry weight of the cement.

Shelf Life: 12 months in the above conditions. Please note: the use of this product after the end of the declared storage period may increase the risk of an allergic reaction. High temperatures and high humidity will lead to a reduced shelf life.

All tiling should follow the correct British/European standard, and incorporate movement joints as specified therein.

As with all raw materials, colour variation may occur. Please note this does not affect the consistency or characteristics of the enclosed product.

HEALTH & SAFETY

Please ensure that appropriate PPE is used when preparing, mixing and applying products. Always wash hands before consuming food and make sure that materials are kept safely out of reach of children and animals. Please dispose of packaging and waste appropriately. A full Material Safety Data Sheet relating to this product is available from www.instarmac.co.uk.

Manufactured by **Instarmac Group plc**

Danny Morson Way, Birch Coppice Business Park, Dordon, Tamworth, Staffordshire B78 1SE

Tel: +44 (0)1827 872244 Fax: +44 (0)1827 874466. Enquiries: email@instarmac.co.uk Visit: www.instarmac.co.uk

Version6.04.2015

An **INSTARMAC** Brand